



ROKIPLAS 2000



DESCRIPTION

Rough finish coating formulated from acrylic polymers for exterior decoration, waterproofing and protection of facades and walls. Excellent resistance to inclement weather.

ADVANTAGES

- ✓ Good breathability.
- ✓ Excellent adherence, prevents blistering on surfaces such as fibrocement, concrete, brickwork, mortar, tile, ceramics, etc.
- ✓ Weather resistant, withstands sunlight, cold and rain.
- ✓ Breathable to water moisture.
- ✓ Excellent resistance to wet rubbing.
- ✓ Water-repellent.
- ✓ Tested at Laboratorios Geocisa, report number: P-02/01565.
- ✓ Up to ten years' guarantee on façades.
- ✓ Mould-resistant formulation against mould, algae and discoloration.

RECOMMENDED USES

Ideal for painting all types of building surfaces including facades, walls, patios, etc. Exterior and interior.

PRESENTATION

Colours: White and colour chart, coating base D, TR, and TR IN.
Special colours available upon request using the Pinay paint mixer system
Textured finish colours available upon request and from colour chart
Finish: Matt.
0.75 L, 4 L and 15 L tubs.

TECHNICAL CHARACTERISTICS

Composition: Fixed vehicle acrylic polymer resins

Pigments: titanium dioxide and selected extender oils.

Density: 1.52± 0.02 Kg/L

Solid volume: 62 ± 2%.

Coverage: 10 – 12 m²/Lt per coat (Approximately, depending on surface requirements).

Drying: To the touch in 1 to 2 hours
Total 24 hours
Repaint After 24 hours at 20 °C.

APPLICATION

Coats: 2 or more as required.

Dilution: 15-30 % first coat and up to 10% for successive coats.

Application temperature: Between 5 and 30 °C.

Painting tools: Spray gun, airless, wide brush, narrow brush, roller, etc.

SURFACE PREPARATION

All new surfaces must be dust free, clean, dry and free of salt bloom.

For old surfaces, as well as the above, remove loose flaky paint. When applied over old paint, unstable or cracked surfaces must be sanded, filled and levelled with the appropriate product from the Pinayplast range. If the surface is powdery or there are differences in absorption, first apply an acrylic fixer to create a homogenous surface, particular with strong colours.

STORAGE

Easy to mix by shaking after 12 months' storage in a sealed container. Does not form skin or lumps. Keep away from temperatures below 5 °C.

SAFETY

Consult the label and the Safety Data Sheet.



Pinturas Ayelenses s.l.
P.I. San José, s/n / 46812
Ayelo de Malferit / Valencia / Spain
t. 96 236 02 92 / f. 96 236 06 01
pinturaspinay.com
info@pinturaspinay.com