



## WATERPROOFER FOR TERRACES WITH FIBRE



### DESCRIPTION

Flexible waterproofing paint formulated with acrylic polymers with fibre incorporated. Free from asphalt products.

### ADVANTAGES

- ✓ Once set and dry it forms a completely waterproof, flexible barrier.
- ✓ Excellent adherence to surfaces such as fibre cement, concrete, brickwork, mortar, ceramic tiles, etc.
- ✓ Excellent resistance to weathering, withstands sunlight, rain and cold.
- ✓ Can be walked on 15 days after drying.
- ✓ Adapts to all types of surfaces.
- ✓ Absorbs expansion and contraction due to temperature changes.
- ✓ The fibreglass enhances its mechanical properties.
- ✓ Does not require geotextile backing.

### RECOMMENDED USES

Ideal for waterproofing terraces, roofs, decking of all types such as concrete, mortar, fibre cement, etc.

For restoring and repainting old asphalt waterproof barriers. For best results, we recommend reinforcing with fibreglass or polyethylene fibre geotextile.

For waterproofing terraces with soldered horizontal drainage

Waterproofing water tanks or rain channels not designed for drinking water.

### PRESENTATION

Colours: White, red, green and grey.

Finish: Silk matt.

4 and 14 L tubs.

### TECHNICAL CHARACTERISTICS

**Composition:** Fixed vehicle: Acrylic copolymer resins.  
Pigments: Titanium dioxide and selected extender oils.  
Solvent: Water.

---

**Density:** 1.30 ± 0.02 Kg./L.

---

**Solid volume:** 62 ± 2%.

---

**Performance:** Depending on thickness applied, varies depending on surface and condition. We recommend using between 1.5-2 Kg /m<sup>2</sup>

---

**Drying:** To the touch 3-4 hours.  
Repaint: after 24 hours (under normal conditions).

**Wet rub fastness:** Class 2 in compliance with UNE-EN 13300:2001.

#### APPLICATION

**Coats:** First coat diluted with 5-10 % water, depending on surface condition  
Apply at least two opposing coats without diluting

**Application temperature:** Between 5 and 30 °C.

---

**Painting tools:** Spray gun, airless, wide brush, narrow brush, roller, etc.  
Shake vigorously before use

#### SURFACE PREPARATION

All surfaces must be dust and rust free, clean and dry. Eliminate any element which affects adherence.

Large cracks (wider than 1 mm) must be filled with flexible filler appropriate for use. Smaller cracks can be flooded with the product during the first coat.

#### STORAGE

Easy to mix by shaking after 12 months' storage in a sealed container. Does not form skin, gel or lumps. Keep away from temperatures below 5 °C.

#### SAFETY

Consult the label and the Safety Data Sheet.



Pinturas Ayelenses s.l.  
P.I. San José, s/n / 46812  
Ayelo de Malferit / Valencia / Spain  
t. 96 236 02 92 / f. 96 236 06 01  
pinturaspinay.com  
info@pinturaspinay.com