



## CHLORINATED RUBBER ENAMEL



### DESCRIPTION

Monocomponent enamel paint for floors, formulated from chlorinated rubber resins, abrasion resistant and excellent adherence to concrete, fibre cement and metal surfaces.

### ADVANTAGES

- ✓ Excellent adherence to concrete, cement and similar, industrial buildings.
- ✓ Quick drying.
- ✓ For indoor use.
- ✓ Weather resistant: rain, sunlight and atmospheric pollution.
- ✓ Dust-free finish.
- ✓ Hardwearing, impact and abrasion resistant.

### RECOMMENDED USES

Ideal for painting road marking, car parks and garages, etc. which do not require extreme toughness.

Paint on asphalt, concrete and cement.

Excellent resistance even on surfaces with low porosity

Poor resistance to diesel, brake fluid and lubricants

Protects buildings against polyurethane foam

### PRESENTATION

Colours: White, Tr base, grey, green, red and any colour to order.

Finish: Semi matt.

4 and 15 L tubs.

### TECHNICAL CHARACTERISTICS

**Composition:** Fixed vehicle – Chlorinated rubber resin.

Pigments: Mineral and organic.

Solvent: Blend of hydrocarbons.

**Density:** 1.15 -1.3 Kg./L. depending on colour.

**Coverage:** 8 – 12 m<sup>2</sup>/Lt. (Approx. depending on surface absorption).

**Drying:** To the touch 30 minutes.  
Total 3-4 hours  
Repaint: 6 hours at 20 °C.

#### APPLICATION

**Coats:** 2

**Recommended thickness:** 40-55 microns per coat.

**Dilution:** 30-40% first coat, 10 % subsequent coats with polyurethane solvent.

**Application temperature:** 5 to 30 °C.

**Painting tools:** Brush, roller and spray gun.  
Mix well before use.

#### SURFACE PREPARATION

For concrete surfaces, the top layer must be stripped with steel brushes, acid cleanser or orbital sander, etc. proceed as for polished cement to open the pore. Old surfaces must free of old paint, grease, etc. and then proceed as for new surfaces.

Despite its excellent adherence, prime with Pinay two-component primer as a bonding and then apply two coats of chlorinated rubber enamel.

Surfaces must be clean, dry and free of grease and floor temperature must be above 5° C.

**Metal surfaces:**

Must be clean, thoroughly rust and grease free and dry to ensure good adherence.

Prime first with shop primer or two-component epoxy primer and then apply two coats of chlorinated rubber enamel.

Painted surfaces should be sanded to remove loose and flaky paint and then cleaned.

Check a small area for adherence and compatibility before painting.

#### STORAGE

Easy to mix by shaking after 12 months' storage in a sealed container. Does not form skin, gel or lumps. Keep away from temperatures below 5 °C..

#### SAFETY

Consult the label and the Safety Data Sheet.



Pinturas Ayelenses s.l.  
P.I. San José, s/n / 46812  
Ayelo de Malferit / Valencia / Spain  
t. 96 236 02 92 / f. 96 236 06 01  
pinturaspinay.com  
info@pinturaspinay.com